

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 61-215206

(43)Date of publication of application : 25.09.1986

---

(51)Int.Cl.

C01B 25/36  
// B01J 27/18  
C10G 45/04

---

(21)Application number : 60-054003

(71)Applicant : CHIYODA CHEM ENG & CONSTR  
CO LTD

(22)Date of filing : 18.03.1985

(72)Inventor : ONO TAKEO  
HIGASHI TAKETO  
OGUCHI YOSHIHIRO  
KAWAKAMI MADOKA

---

## (54) PRODUCTION OF POROUS ALUMINA PHOSPHIA

(57)Abstract:

PURPOSE: To obtain an alumina phosphia carrier having sharp pore-size distribution and improved mechanical strength, by producing aluminum hydroxide, adding a phosphorus compound thereto and forming a complex under a specific condition.

CONSTITUTION: Aluminum hydroxide gel is produced e.g. by neutralizing an aqueous solution containing an aluminum compound. A phosphorus compound is added to the gel at an atomic ratio (Al/P) of 0.3W30, and the mixture is aged at 50W100°C and ≤7pH for 5minW24hr. The obtained alumina phosphia gel is washed, filtered, formed and calcined.

---

## LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's